

MOLYKOTE® TP-42 Paste

Light-colored adhesive grease-paste with solid lubricants for metallic friction combinations

Features

- High load-carrying capacity
- Particularly adhesive
- Particularly resistant to washout by water and metal machining emulsions
- Prevents stick-slip
- Good corrosion protection
- Excellent protection against galling

Composition

- Mineral oil
- Synthetic oil
- Lithium soap
- Solid lubricants
- Adhesion improver

Applications

Sliding surfaces exposed to high pressure loadings and subject to the influence of water of metal machining emulsions.

Recommended and successfully used by leading clamping-element manufacturers, especially for chucks on metal processing machines.

How to use

The sliding surfaces should be cleaned. The paste should then be applied with a suitable brush, rag or grease gun. It should not be mixed with greases or oils.

Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

Usable life and storage

When stored at or below 20°C in the original unopened containers, this product has a usable life of 60 months from the date of production.

Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

Standard ⁽¹⁾	Test	Unit	Result
	Color		Light beige
Penetration, density, viscosity			
ISO 2137	Unworked penetration	mm/10	265-300
ISO 2811	Density at 20°C	g/ml	1.19
Temperature			
	Service temperature ⁽²⁾	°C	-25 to +250
ISO 2176	Drop point	°C	125
ASTM D1478-80	Low-temperature torque test at -20°C		
	Initial break-away torque	Nm	224x10 ⁻³
	Torque after 20 minutes running time	Nm	59x10 ⁻³
DIN 51 805	Kesternich method - flow pressure at -20°C	mbar	740
Load-carrying capacity, wear protection, service life			
	Four-ball tester (VKA)		
DIN 51 350 pt.4	Weld load	N	3,000
DIN 51 350 pt.5	Wear under 800 N load	mm	0.9
	Almen-Wieland machine		
	OK load	N	20,000
	Friction force	N	1,710
Coefficient of friction			
	Press-fit test μ =		0.09
Resistance			
DIN 51 807 pt.1	Water resistance, static		2-90

⁽¹⁾ASTM: American Society for Testing and Materials. ISO: International Standardization Organization. DIN: Deutsche Industrie Norm.

⁽²⁾Thermal stability of solid lubricant.

Continued on next page



تامین صنعت پارلاتک
www.parla-tech.com
info@parla-tech.com

Typical properties (continued)

Standard ⁽¹⁾	Test	Unit	Result
Corrosion protection			
DIN 51 802	SKF-Emcor method		
	Degree of corrosion		0-1
Oil separation - evaporation			
DIN 51 817	Oil separation, standard test	%	1.5

⁽¹⁾ASTM: American Society for Testing and Materials. ISO: International Standardization Organization. DIN: Deutsche Industrie Norm.

Packaging

This product is available in different standard container sizes. Detailed container size information should be obtained from your nearest MOLYKOTE® sales office or MOLYKOTE® distributor.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.
© 1997-2020 DuPont.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.